

LION D.O.O.
PARTIZANSKA 37, 78400 GRADISKA, BOSNA I HERCEGOVINA

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : (A) BONDED FABRIC

Sample Color : (A) 203

Composition : (A) 100% POLYESTER

Style No. : IBIS

Order No. : 323-21

Country of Origin : China

Proposed Care Instruction : -


Sample Receiving Date : Feb 17, 2022

Testing Period : Feb 18, 2022 - Mar 01, 2022

Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the sample(s) tested, for further details, please refer to the following page(s).

Test Performed : Selected test(s) as requested by applicant

Signed for and on behalf of
SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd Testing Center



Alice Wang (Authorized Signatory)



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

Test Result

Colour Fastness To Light

(EN ISO 105-B02:2014; Method 2 (Modified), use Xenon arc lamp, Exposure Cycle: A1, no flip-flop mode was used)

Comparison upto blue wool reference 4

-	Unit	A
Grade(B.W.S)	-	4

Colour Fastness To Rubbing

(EN ISO 105-X12:2016; Size of rubbing finger: 19x25.4mm)

As Received

-	Unit	A
Dry Staining	Grade	4-5
Wet Staining	Grade	4-5

Remark: Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is worst and 5 is best.

Abrasion Resistance

(EN ISO 12947-2:2016; Martindale Abrasion & Pilling Tester, Pressure: 12kPa)

As Received

-	Unit	A
The quoted result	Rubs	>30000

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com



Pilling Resistance

(EN ISO 12945-2:2000; Martindale Abrasion & Pilling Tester, Total load applied 415g)

As Received

After 500 Revolutions

-	Unit	A
Pilling Rating	-	4-5

After 1000 Revolutions

-	Unit	A
Pilling Rating	-	4-5

After 2000 Revolutions

-	Unit	A
Pilling Rating	-	4-5

After 5000 Revolutions

-	Unit	A
Pilling Rating	-	4-5

Remarks : Pilling Rating

- 5 No change
- 4 Slight change fuzzing and/or partially formed pills
- 3 Moderate change fuzzing and/or moderate pilling, pills of varying size and density partially covering the specimen surface
- 2 Distinct surface fuzzing and/or distinct pilling, pills of varying size and density covering a large proportion of the specimen surface
- 1 Dense surface fuzzing and/or severe pilling, pills of varying size and density covering the whole of the specimen surface

Tensile Strength

(EN ISO 13934-1:2013; Strip method)

-	Unit	A
Warp/Length	N	580
Weft/Width	N	890

End of Report



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
 Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com
 SGS-CSI Standards Technical Services (Shanghai) Co., Ltd. 3rd Building, No.889, Yishan Road, Xuhui District Shanghai, China 200233 t (86-21) 61402666 f (86-21) 64958763 www.sgs.com.cn
 Testing Center for Textiles Technical Services (Shanghai) Co., Ltd. 中国·上海·徐汇区宜山路889号3号楼 邮编: 200233 t (86-21) 61402666 f (86-21) 64958763 e sgs.china@sgs.com

LION D.O.O

ADD:PARTIZANSKA 37,78400 GRADISKA BOSNIA I HERCEGOVINA

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : Bonded fabric,with white TC backing for upholstery
Style No. : IBIS

Proposed Care Instruction : -

Test Performed : Selected test(s) as requested by applicant
* * * * *


Sample Receiving Date : Sept 13, 2022
Testing Period : Sept 13, 2022 - Sept 16, 2022
Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. For further details, please refer to the following page(s).

Conclusion

Colour Fastness To Rubbing	M
Colour Fastness To Light	M
Seam slippage	M
Tearing Strength	M

Remarks: M=Meet General's Requirement F=Below Client's Requirement
 *=No Specified Requirement M#=Meet Client's Requirement

Signed for and on behalf of
SGS-CSTC Standards Technical Services (Shanghai) Co. Ltd



Hattie Chen
Account Executive



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

Test Result

Requirement

Colour Fastness To Rubbing

(EN ISO 105-X12:2016; Size of rubbing finger:16mm diameter)

Dry staining	4-5	Min.3
--------------	-----	-------

Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good

Colour Fastness To Light

(EN ISO 105-B02:2014; use Xenon arc lamp,exposure cycle A1, no flip-flop mode was used)

Grade (B.W.S)	4	Min.4
---------------	---	-------

Seam Slippage

(EN ISO 13936-2:2004;)

<u>Seam Slippage At 180N</u>	<u>Unit</u>	<u>(A)</u>
Length // Seam	mm	2.3
Width // Seam	mm	2.2

Tearing Strength

(EN ISO 13937-3:2000;)

	<u>Unit</u>	<u>(A)</u>
Warp/Length Yarns Torn	N	Untearable in this direction
Weft/Width Yarns Torn	N	89

*** End of Report ***

